

**G O L D E N   Y E L L O W**



**3 8 H**

Soft silicone rubber for general purpose and high flexibility.

Excellent Tear and Tensile Strength!

Golden Yellow produce waxes with a very smooth finish that won't stick to the mold.

Excellent return to shape, or "memory".

High thermal conductivity means that waxes cool more quickly, increasing the number of wax patterns that can be made per hour.

**PROPERTIES**

**VALUES**

Vulcanisation Temperature	165-175°C
Vulcanisation Time	15 mins / 6mm. of mold thickness
Shore A Hardness	38+-2
Tear Strength	18.0 N/mm.
Tensile Strength	6.0 N/mm <sup>2</sup>
Elongation	800%
Shrinkage	<3%

**STORE AWAY FROM HEAT & DIRECT SUNLIGHT**

(Should store in room temperature under 25°C)