

L I G H T B L U E



3 8 L

Medium Hardness silicone rubber for general purpose.

Excellent Tear and Tensile Strength.

Light blue produce waxes with a smooth high shine finish that won't stick to the mold.

Excellent return to shape, or "memory".

High thermal conductivity means that waxes cool more quickly, increasing the number of wax patterns that can be made per hour.

PROPERTIES

VALUES

| | |
|---------------------------|----------------------------------|
| Vulcanisation Temperature | 90-100°C |
| Vulcanisation Time | 15 mins / 6mm. of mold thickness |
| Shore A Hardness | 38+-2 |
| Tear Strength | 22 N/mm. |
| Tensile Strength | 7.0 N/mm ² |
| Elongation | 700% |
| Shrinkage | <1% |

STORE AWAY FROM HEAT & DIRECT SUNLIGHT

(Should store in room temperature under 25°C)